

In the Abstract

Kindly amend the Abstract with the following Abstract marked-up to show the changes that have been made.

The present invention relates to a warp knit having excellent touch and a process of preparing such a warp knit. The present invention provides a warp knit ~~comprising~~ consisting of three layers, namely a front surface layer, a rear surface layer, and an intermediate layer arranged between the front surface layer and the rear surface layer, the front surface layer consisting of ultra fine yarn with monofilament denier of 0.01– to about 0.3 denier, the intermediate layer consist of spandex elastic yarn, the rear surface layer consisting of synthetic yarn ~~or high shrinkage yarn~~ with monofilament denier of 1– to about 5 denier, wherein the recovery rate of elongation in the directions of wale and course is 25 – to about 60 %. The warp knit according to the present invention is can be used to manufacture artificial leathers or ladies' clothes.